



# 5100 4T 15W-50

## High Performance Motorcycle Lubricant

### Technosynthese® - Ester

#### TYPE OF USE

Street & road bikes, trails, off road bikes, enduro, trial...fitted with 4 stroke engines, integrated gearbox or not, wet or dry clutch, engines meeting Euro 2 or Euro 3 emission regulation, fitted with exhaust gas after treatment systems : catalytic converters, air injection into exhaust pipe...

Recommended for specific BMW, DUCATI engines requiring SAE 15W-50 viscosity grade oil.

Other uses: street bikes without catalytic converters, ATV's, UTV's...

#### PERFORMANCE

STANDARDS                      API SM / SL / SJ / SH / SG  
SPECIFICATION                JASO MA2 under N° M033MOT114

#### **Protection**

Technosynthese® lubricant reinforced by Ester base stock to warranty anti-wear properties and improve gear protection and life time.

Improved oil film resistance at high temperatures.for engine durability.

Grade 50 at hot temperature, specially designed for big bore engines, thumpers, twins, multicylinders...

Optimized Phosphorus and Sulphur content (JASO MA2 < 1200 ppm) for better operating conditions of catalytic converters.

The innovative anti wear additives package provides excellent gearbox protection. FZG Gear Test results: Pass FLS 14. The **FZG** (Forschungsstelle für Zahnrad und Getriebebau) Test, evaluates fluid lubricating and wear protection properties at the interface of a loaded set of gears.

#### **Comfort**

JASO has created its own 4-stroke motorcycle standard -JASO T903- which has three grades MA, MA1 and MA2.

JASO MA2 offers the most efficient friction levels to guarantee the clutch engagement during the three riding modes: Starting, Acceleration and Constant Speed.

#### RECOMMENDATIONS

Drain interval : according to manufacturers' recommendations and tune to your own use.

Can be mixed with synthetic or mineral lubricants.

#### PROPERTIES

Colour	Visual	Amber
Viscosity grade	SAE J 300	<b>15W-50</b>
Density at 20°C (68°F)	ASTM D1298	0.877
Viscosity at 40°C (104°F)	ASTM D445	138.7 mm <sup>2</sup> /s
Viscosity at 100°C (212°F)	ASTM D445	18.3 mm <sup>2</sup> /s
Viscosity Index	ASTM D2270	148
Pour point	ASTM D97	-30°C / -22°F
Flash point	ASTM D92	232°C / 449°F
TBN	ASTM D2896	7.5 mg KOH/g

We retain the right to modify the general characteristics of our products in order to offer to our customers the latest technical development.

Product specifications are not definitive from the order which is subject to our general conditions of sale and warranty. – Made in France

MOTUL - 119 Bd Félix Faure - 93303 AUBERVILLIERS CEDEX - BP 94 – Tel : 33 1 48 11 70 00 - Fax : 33 1 48 33 28 79. Web Site : [www.motul.com](http://www.motul.com)

05/13