

MOTUL 300V FACTORY LINE OFF ROAD 5W-40 4T

Lubricant for racing motorcycles Racing Motorcycle Lubricant Ester Core®

TYPE OF USE

- 4T racing motor oil developed for factory and high-performance stock off-road motorcycles.
- Increased torque for ultimate motricity control and acceleration.
- Ester Core® technology for maximum adherence of the oil film enhancing reliability.

API / JASO: above latest existing standards.

Applications: Motorcycle, ATV / UTV / SxS, Personal Watercraft, Snowmobile.

PERFORMANCES

STANDARDS

Above existing Motorsport standards / Wet clutch compatibility tested according to JASO T903:2023, level MA2

ESTER Core® TECHNOLOGY

For decades MOTUL has developed high performance synthetic Ester based lubricants.

By selecting esters over other high performance synthetic base stocks and combining them with an innovative additive package, MOTUL has created a perfect synergy.

This most advanced *ESTER* Core[®] Technology allows maximum power output of the engine without compromising reliability and wear.

- Extra engine torque up to 2.5%.
- Optimized clutch friction indexes for improved life time and better traction in difficult conditions, sand, snow, mud...

Outstanding gearbox protection: Thanks to the innovative anti-wear additives package. FZG Gear Test results: Pass FLS>14. The **FZG** (Forschungsstelle für **Z**ahnrader und **G**etriebebau) Test, evaluates fluid lubricating and wear protection properties at the interface of a loaded set of gears. Lubricants are then graded based on their "Failure Load Stage" or FLS rating from FLS 1 (very poor result) up to FLS 14 (outstanding result).

- Stable oil pressure whatever running conditions.



MOTUL 300V FACTORY LINE OFF ROAD 5W-40 4T

Lubricant for racing motorcycles Racing Motorcycle Lubricant Ester Core®

RECOMMENDATIONS

 $For optimum \ engine \ and \ gearbox \ performance, \ avoid \ mixing \ with \ other \ synthetic \ or \ mineral \ lubricants.$

Oil change: according to your own use.

PROPERTIES

Color	Visual	Green Fluo
Viscosity grade	SAE J 300	5W-40
Density at 20°C (68°F)	ASTM D1298	0.854
	ASTM D445	72.0 mm²/s
Viscosity at 40°C (104°F)		
	ASTM D445	13.0 mm²/s
Viscosity at 100°C (212°F)		
HTHS viscosity at 150°C (302°F)	ASTM D4741	4.2 mPa.s
	ASTM D2270	184.0
Viscosity Index		
	ASTM D97	-48.0 °C / -54.0 °F
Pour point		
TBN	ASTM D2896	8.7 mg KOH/g
Flash point	ASTM D92	220.0 °C / 428.0 °F