

SUPRACO ELECTRIC 40A

Verformung

DESCRIPTION

SUPRACO ELECTRIC 40 A ist ein nicht wassermischbarer Schmierstoff mit einem niedrigen Gefrierpunkt und hervorragenden Korrosionsschutzeigenschaften.

ANWENDUNGEN

SUPRACO ELECTRIC 40A ist ein helles, nicht wassermischbares Öl zur Imprägnierung von Stahlblechen, Induktionskernen, Kontakten, Unterbrechern und Schneiden von Stahlblechen mit Silizium (Brinellhärte 200).

VORTEILE

- Vermeidung von Blechverformungen während des Schneidvorgangs
- SUPRACO ELECTRIC 40 A can be used for degreasing and impregnation before assembly
- Reduzierter Verbrauch (50 mg pro Schaltvorrichtung)
- Unempfindlich gegenüber Feuchte: verhindert Abblättern und Oxidation

TECHNICAL INFORMATION

NAME	UNITS	STANDARDS	SUPRACO ELECTRIC 40A
Farbe	-	Visuell	Bräunlich
Aspect	-		Transparent
Dichte bei 20°C	-	ISO 12185	0.873
Viskosität bei 40°C	mm ² /s	ASTM D445	45.0
Flammpunkt	°C	ASTM D92	>220
Pourpoint	°C	ASTM D97	-6.0
Copper Strip Corrosion	-	NTF M 07105	1A
Storage	-		trocken und frostfrei

These characteristics are given only for information and can be updated over time.



DATA SHEET

SERVICES AND EQUIPMENT

In addition to its product ranges, MotulTech can provide tools and services for the maintenance and monitoring of your lubricants. Please contact your technical sales representative for more information.