



## MOTULTECH CADREX DR 40 SC

### DEFORMATION

### DESCRIPTION

**CADREX DR 40 SC** is a chlorine-free, neat oil designed for drawing, bending, reshaping and fine blanking on all ferrous and non-ferrous metals, under low-duty conditions.

### APPLICATIONS

For all parts arriving on assembly lines or elements used to make sub-assemblies (sheet steel, bare or coated beforehand with zinc or zinc alloys, sheet aluminum, etc.). Ready to use, it can be used by spraying, brushing or dipping.

### ADVANTAGES

- Does not yellow under an HPRL lamp.
- If it is not rinsed off, CADREX DR 40 SC provides temporary protection from all subsequent corrosion, for treated metals.
- Easy to clean before painting application.
- Can protect against corrosion for 1 to 2 months under shelter.

### TECHNICAL INFORMATION

TECHNICAL CHARACTERISTICS	UNITS	METHOD	CADREX DR 40 SC
Aspect	-		Light
Storage	-		in frost-free, dry place

These characteristics are given only for information and can be updated over time.

### SERVICES AND EQUIPMENT

In addition to its product ranges, MotulTech can provide tools and services for the maintenance and monitoring of your lubricants. Please contact your technical sales representative for more information.



#### Important Notice

All information and rules about health, safety and the environment are mentioned on the safety data sheet. It provides information about risks, safety procedures and first aid emergency rules. It clarifies all procedures to implement in the case of an accidental spillage, and for the disposal of the product and its effects on the environment. The safety data sheet is available on [www.motul.com](http://www.motul.com).

Our product contains natural additives which are likely to modify the colour of the concentrates without altering its performance. The specifications of our products are definite only at the time of order, and are subject to our general sale and guarantee conditions. To give our customers the latest technical developments, the general characteristics of our products may vary.