MOTUL MOTYLGEAR 75W-80

زيوت تشحيم علبة التروس
تقنية Technosynthese

أنواع الأستخدام

يوصى به خصيصًا لصناديق التروس التي يصعب تغيير تروسها وصناديق التروس من طراز بيجو وسيتروين ورينولت... جميع صناديق التروس الميكانيكية، وصناديق التروس المتزامنة أو غير المتزامنة، وصناديق التروس/التفاضلية وصناديق التروس التحويلية بدون نظام انزلاق محدود يعمل تحت الصدمات والأحمال الثقيلة وسرعات الدوران المنخفضة أو الأحمال المتوسطة وسرعات الدوران العالية.

مستويات الاداء

زيت تشحيم عالي الضغط لحماية فعالة ضد التآكل معزز بمواد أساسية صناعية لمقاومة أفضل في درجات الحرارة العالية وعمر أطول. يبقى بدرجة لزوجة 80 بعد اختبار القص KRL لمدة 20 ساعة كما هو مطلوب من معيار SAE J306. قوة تشحيم عالية جدًا تقلل من الاحتكاك والتآكل. درجة اللزوجة 80 عند درجة حرارة عالية تقلل من سحب علبة التروس ومن ثم استهلاك الوقود. سائل عند درجة حرارة منخفضة للسماح بتغيير التروس بسهولة عندما يكون صندوق التروس باردًا. يتطلب جهدًا أقل على ذراع التروس لتغيير التروس. مناسب لأي نوع من الأختام والمواد الصفراء المستخدمة في تصميم علب التروس. مضاد للتآكل ومضاد للرغوة.

التوصيات

تغيير الزيت: وفقًا لمتطلبات الشركات المصنعة واضبطه وفقًا لاستخدامك الخاص.

المواصفات

Viscosity grade	SAE J 306	75W-80
(Density at 20°C (68°F		0.862
(Viscosity at 40°C (104°F	ASTM D445	mm²/s 57.1
(Viscosity at 100°C (212°F	ASTM D445	mm²/s 10.1
Viscosity Index	ASTM D2270	164.0
Pour point	ASTM D97	C / -60.0 °F° 51.0-
Flash point	ASTM D92	C / 406.0 °F° 208.0

We retain the right to modify the general characteristics of our products in order to offer to our customers the latest technical development. br\>
Product specifications are definitive from the order which is subject to our general conditions of sale and warranty. Made in FRANCE

- MOTUL - 119 Bd Félix Faure - 93303 - Aubervilliers Cedex - BP 94 - FRANCE - Tel: 33 1 48 11 70 00 - Fax: 33 1 48 33 28 79

MOTUL MOTYLGEAR 75W-80

زيوت تشحيم علبة التروس
تقنية Technosynthese

STANDARDS	
API	GL-4, GL-5
MIL-L	D 2105

We retain the right to modify the general characteristics of our products in order to offer to our customers the latest technical development. br\>
Product specifications are definitive from the order which is subject to our general conditions of sale and warranty. Made in FRANCE

- MOTUL - 119 Bd Félix Faure - 93303 - Aubervilliers Cedex - BP 94 - FRANCE - Tel: 33 1 48 11 70 00 - Fax: 33 1 48 33 28 79

motul.com