

## **RUBRIC HFC 40**



Synthetic Hydraulic Fluid

#### **DESCRIPTION**

**RUBRIC HFC 40** is a fire-resistant, hydraulic fluid which belongs to the HFC group. It contains an aqueous solution, a combination of glycols of different chain lengths as well as special additives for wear resistance and corrosion protection etc.

#### **APPLICATIONS**

**RUBRIC HFC 40** can be applied in all areas where there is a risk of a fire hazard, such as the steel industry in forging shops, heat treatment shops, casting shops – especially in die casting shops – in coal mines, but it can also be used in applications where good bio-degradability of the hydraulic fluid is important.

#### **ADVANTAGES**

- Excellent fire resistance properties.
- High lubricity and anti-wear characteristics.
- Excellent corrosion protection.
- Long term stability.

#### TECHNICAL INFORMATION

TECHNICAL CHARACTERISTICS	UNITS	METHOD	RUBRIC HFC 40
рН	-		9.6

These characteristics are given only for information and can be updated over time.

### SERVICES AND EQUIPMENT

In addition to its product ranges, MotulTech can provide tools and services for the maintenance and monitoring of your lubricants. Please contact your technical sales representative for more information.



# DAIA

#### Important Notice

All information and rules about health, safety and the environment are mentioned on the safety data sheet. It provides information about risks, safety procedures and first aid emergency rules. It clarifies all procedures to implement in the case of an accidental spillage, and for the disposal of the product and its effects on the environment. The safety data sheet is available on www.motul.com.

Our product contains natural additives which are likely to modify the colour of the concentrates without altering its performance. The specifications of our products are definite only at the time of order, and are subject to our general sale and guarantee conditions. To give our customers the latest technical developments, the general characteristics of our products may vary.