

MOTULTECH RUBRIC HM 46



HYDRAULIC SYSTEMS زيت هيدروليكي - مضاد للتآكل ISO VG 46 معدي

أنواع الاستخدام

روبك ايج ايم 46 (RUBRIC HM 46) هو زيت هيدروليكي ممتاز مضاد للتآكل والتآكل والأكسدة ومناسب لتزيت الأنظمة الهيدروليكية التي تعمل في ظل ظروف قاسية.

مستويات الاداء

يعتبر روبك ايج ايم 46 (RUBRIC HM 46) مناسبًا لجميع أنواع الأنظمة الهيدروليكية، والآلات التي تعمل في ظروف قاسية للغاية: آلات البناء، والآلات الزراعية، والمعدات الصناعية... كما أنه مناسب لجميع أنواع المضخات: المكابس المحورية، والمكابس الشعاعية، وأنظمة التروس، والشفرات.

التوصيات

تصريف الزيت: وفقًا لمتطلبات الشركة المصنعة ونتائج اختبار الزيت. يمكن خلطه بالزيوت التخليقية والمعدنية.

المواصفات

30.0	ASTM D877	Dielectric strength
Clear & bright	Visual	Color
46	ISO	Viscosity grade
g/mL 0.87	ISO 12185	(Density at 20°C (68°F
mm²/s 46.0	ASTM D445	(Viscosity at 40°C (104°F
mm²/s 6.9	ASTM D445	(Viscosity at 100°C (212°F
110.0	ASTM D2270	Viscosity Index
C° 24.0-	ASTM D97	Pour point
C° 215 ≤	ASTM D92	Flash point

We retain the right to modify the general characteristics of our products in order to offer to our customers the latest technical development. br>

Product specifications are definitive from the order which is subject to our general conditions of sale and warranty. Made in FRANCE

06/25

- MOTUL - 119 Bd Félix Faure - 93303 - Aubervilliers Cedex - BP 94 - FRANCE - Tel: 33 1 48 11 70 00 - Fax: 33 1 48 33 28 79

motul.com

MOTULTECH RUBRIC HM 46



HYDRAULIC SYSTEMS
زيت هيدروليكي - مضاد للتآكل ISO VG 46
معدي

STANDARDS	
NF E 48603 HM	AFNOR
part 2 HLP 524 51	DIN
categories HM, 6743-4 categories HM 11158	ISO
PRODUCTSSTCUDORP	
DENISON HF-0	Parker Denison

We retain the right to modify the general characteristics of our products in order to offer to our customers the latest technical development. br\>

Product specifications are definitive from the order which is subject to our general conditions of sale and warranty. Made in FRANCE

- MOTUL - 119 Bd Félix Faure - 93303 - Aubervilliers Cedex - BP 94 - FRANCE - Tel: 33 1 48 11 70 00 - Fax: 33 1 48 33 28 79